

Synthesis the Structural and Optical properties of Nickel Oxide Nanoparticles

Muhammad Arslan Naseer*

Department of Physics Faculty of Sciences The Superior University Lahore Pakistan
Email: muhammadarslannaseer65@gmail.com

Muhammad Rizwan Aslam

Department of Physics Faculty of Sciences The Superior University Lahore Pakistan

Thiraj Ahmed

Department of Physics Faculty of Sciences The Superior University Lahore Pakistan

Zaki Nawaz

Department of Physics Faculty of Sciences The Superior University Lahore Pakistan

Ayesha Ashraf

Department of Physics Faculty of Sciences The Superior University Lahore Pakistan

Rana Muhammad Bilal

Department of Physics Government College University Faisalabad, Punjab, Pakistan

ABSTRACT

The Nickel oxide (NiO) nanoparticles were manufactured through a microwave-accelerated combustion process which is designed to reduce the need for a conventional continuous heating. The produced NiO material sustain strengthening at 200°C to 400°C. The average crystallite size for both NiO samples was determined to be 20 nm or 30 nm respectively, and the XRD pattern verifies the material's excellent crystallinity. Nevertheless, SEM examination were used to examine the the **study of the shape, size, structure, and physical appearance** of the materials, cells, or organisms which revealed a spherical form with an aggregation matrix. This includes the NiO. Additionally, a thorough FTIR analysis was done to determine the functional group included in the produced samples. Bandgap values are calculated from the UV-Vis absorption spectra computed in that perspective. Similarly, the compound composition were shown in the compound were displayed in the composition. According to the antibacterial analysis, both samples expresses wide-ranging activity against both Gram-positive and Gram-negative category. Therefore, this environmentally friendly synthesized NiO material has antibacterial potential.

Keyword: Nio Nanoparticles, Synthesis, Structural Characterization, Optical Properties, Optical Band Gap

Introduction

Nano scales ranges of the materials that is used widely in many fields of sciences including physics biology, chemistry, and polymers of science [1]. Usually Nickel oxide nanoparticles (NiO) is most important evolution metal oxide nanoparticles with cubical lattice structure that are used in many uses [2]. Nickel oxide (NiO), a considerable transition metal oxide material with a cubic lattice structure is used in several tenders [3]. Battery electrodes, photoelectron devices ion storage materials, gas sensors, magnetic materials thermoelectric materials catalysts fuel cell dye-sensitized photocathodes electro chromic films anticancer properties cytotoxic activity and non-enzymatic glucose sensors are just a few of the numerous applications for NiO nanoparticles (NPs) [4]. Nickel oxides (NiO) nanoparticles are also investigated because nano particles have distinct optical, electronic, and physiochemical properties that set them apart from most nanoparticles in such a way that surface area to volume ratio and electro-optical, magnetic-optical, chemical, and electro magnetical properties [5]. The need for new qualities is that the length change and the what factors also changes when the properties change with their size , length and structure have drawn attention to nanoscale materials as a result of advances in all facets of industry and technology [6]. Due to the surface effects and the quantum size effects, size reduction effects and the majority of the physical characteristics (structural, optical, dielectric thermal etc.) [7].

Many NiO NPs has a lot of the process has a lot of energy, but a lot of a lot of a lot of energy, but a lot of energy, but a lot of energy. There are still problems, such as the limited manufacturing capacity for usage in production lines, even if various techniques have been described to synthesise them while lowering energy consumption [8]. Therefore, in presence to achieve global carbon impartiality, straightforward and economical synthetic approaches are crucial. This approach uses a low NiO NPs We manufactured NiO NPs using acetate-based raw ingredients that do not include hazardous compounds like Cl- or NO₃-, which reduces effluent, even though we chose a straightforward chemical process which is often employed in a manufacture line. Current synthetic procedures that use materials that include hazardous compounds need multiple water washing stages to get rid of such toxins and substantial amount of the wastewater also is produced during the mostly cleaning procedures; however the purify substance is easily washed into water, therefore using acetate-based raw materials can reduce both the time of washing and the amount of wastewater generated [9]. Nickel oxide nanomaterial have drawn a lot of attention about it. Lately due to this broad band gap (3.5-4.0 eV) p-type conductivity [10]. They include smart windows, photo catalysis, anti-microbial activity anti-ferromagnetic film, catalysis electrochemical films, photo electronic devices, gas sensors and so on. Additionally, we compared to micro and macro level NiO particles, nanostructured has better features including the volume effect and also surface effect [11]. However, nickel oxide nanomaterial has been regarded as an affordable semiconductor with long-term stability accessibility, and non-toxicity for the elimination of environmental contaminants from waste water [12]. Additionally, research indicates that nickel nanoparticles have strong antibacterial activity in front of a variety of gram positive and gram negative bacterial strains and also superior antimicrobial impact compared to other metal nanoparticles. According to reports by

Jeyaraj et al., NiO NPs have more potent antibacterial action than silver NPs because the activity of the green synthesised nanostructures mostly depends on the treatment duration, sample dosage, and methodology used [13]. Numerous chemical as well as physical techniques, including as evaporation, the sol–gel method, laser ablation deposition, and spray pyrolysis (SP) can be used to create NiO thin films [14]. Sputtering can be used to deposit NiO thin films with low resistivity ($1.2 \times 10^{-3} \Omega \cdot \text{cm}$). When it comes to creating TCO thin films for small-area coating. It is a more straightforward and economical nonvacuum deposition technique than vacuum deposition.

Experimental detail

Nickel oxide (NiO) nanoparticles were produced by using a suitable chemical precipitation methods. After dissolving the nickel precursor in distilled water, a precipitating agent was added while being continuously stirred. NiO nanoparticles were produced by washing drying, and calcining the precipitate at the proper temperature. The structural properties were examined using x-ray diffraction is used to find crystal structure, crystallite size, and lattice parameters.

Synthesis of Nickel Oxide (NiO) Nano Particles

The production of nickel oxide (NiO) nanoparticles by chemical precipitation method using a suitable nickel salt as precursor. The precursor solution was prepared in distilled water under continuous magnetic stirring. A suitable precipitating agent was added dropwise until the preferred precipitous was formed. The precipitate were filtered, washed three to four times with distilled water, Then dried to remove impurities and moisture. Finally, the dried material was calcined at an appropriate temperature to obtain crystalline NiO nanoparticles. The prepared nanoparticles were then used for further structural, morphological, and optical characterization.

Materials Characterizations

The morphological structural and optical characteristics of the synthesised nickel oxides nanoparticles was studied utilising a variety of diagnostic methods. The X-ray diffraction were used to analyzes the crystal structure and phase purity, while (SEM) were used to analyze the surface morphological and particle distribution. UV–visible spectroscopy in the proper wavelength region was used to examine the optical absorption properties. It is also used to determine the structural band gap from the absorption data. The structure, shape, and optical behaviour of the produced NiO nanoparticles were all thoroughly described by these characterizations.

Results and Discussion

XRD Analysis

At this stage x-ray diffraction were applied to analyze the crystal structure, phase formation, and the synthesized nickel oxide (NiO) nanoparticles. The successful creation of the intended crystalline phase is shown by the measured reflections, which may be indexed to the corresponding crystallographic planes of NiO. The synthesized material's nanoscale crystallite size is linked to the diffraction peaks' widening. Therefore, the XRD results verify the creation of crystalline NiO nanoparticles and

offer crucial details about their structural properties.

The x-ray diffraction patterns of the four nickel oxides nanoparticles samples are displayed. Each sample displays a similar diffraction pattern in spite of variations in heat treatment temperatures. The nickel oxides nanoparticles heat-treated at 300 °C in Figure 3a contain prominent diffraction peaks at <111>, <200>, <220>, <311> and <222> directions, respectively. The <200> direction showed the largest growth among them, suggesting a hexagonal structure with the <200> favored positioning. Moreover in Figure 3b–d the samples heat-treated at 400 °C, 500 °C, and 600 °C revealed diffraction patterns comparable to those of 300 °C. As a result, it is clear that every sample of NiO NPs has the same hexagonal structure.




Figure 1. XRD Patterns of NiO

FTIR Analysis

Fourier Transform Infrared (FTIR) spectroscopy was used to examine the surface chemistry and chemical structure of the synthesized nickel oxide nano particles (g-NiO) samples. The spectra of the samples prepared at 450°C (A1) and 500°C (A2) respectively. The goal of investigation is to clarify how the synthesis temperature affects the material's molecular structure optical properties and functional groups. The optical energy band gap of the manufactured Nickel Oxide (NiO) nanoparticles was determined using Tauc's relation derived from UV-Visible absorption spectroscopy data. The relationship between the absorption coefficient (α) and photon energy ($h\nu$) is expressed as $(\alpha h\nu)^n = A(h\nu - E_g)$ where $n = 2$ corresponds to the direct allowed band transition. As shown in Figure 2, the plot of $(\alpha h\nu)^2$ versus photonic energy $h\nu$ in electron volt displays a sharp absorption edge. By inducing the linear region of the curve to the energy axis at the $(\alpha h\nu)^2 = 0$. The structural and the optical band gap value for the NiO is estimated to 2.5 eV. Band gap reduction compared to bulk NiO (3.4 – to 4.0 eV)

Online ISSN

3007-3197

Print ISSN

3007-3189

<http://amresearchreview.com/index.php/Journal/about>




Figure 2. FTIR of NiO

Can be accredited to quantum internment effect, structural defects and the surface state variations during synthesis.

Morphological Analysis (SEM)

In this section the surface morphology and microstructural characteristics of the nickel oxides samples created at numerous temperatures were examined by using the scanning electron microscopy (SEM). The micrographs gained are shown in Figure. 4. All the images clearly explain a temperature-dependent morphological change from aggregated particles to a clearer layered architecture. At the lowest synthesis temperature of 400 °C, the material is composed of large, not regular, dense agglomerates with an amorphous, rock-like morphology. The surface appears to be rather smooth, and there is no visible porosity or fine structure. This condition is the feature of a intermediately condensed product, where thermal energy initiated the condensation reaction but the polymeric strands were not managed into long sheets. When the temperature is increased upto the 400 °C, the form clearly changes (NiO-400 °C). The big agglomerates start to start to reorganize. As the polymeric network continues to condense, the structure becomes less dense and the surface appears rougher, indicating sheet formation. The sample obtained at 500 °C (NiO-500 °C) illustrates the last step of the morphological progression. The lamellar sheet is a clearly defined, lamellar, sheet. The structure is very graphitic, as evidenced by these twisted and wrinkled NSs. The snapshot appears to be a high porosity between the stacked sheets. The complete poly condensation at 500 °C, which enables the creation of long, thin layers that eventually stack via van der Waals forces, is directly responsible for this morphology. The crucial role thermal energy plays in controlling the exfoliation and self-assembly processes required for the production of graphitic carbon nitride is highlighted by the transition from dense agglomerates to thin nanosheets with increasing temperature.




Figure 3. SEM Analysis (a, b) of NiO

UV- Vis Analysis

In this analysis the optical absorption were applied. The absorption spectra was obtained in the wavelength range of 100–500 nm to evaluate the optical absorption behaviour and electronic evolutions of the produced materials. The acquired spectra confirmed the optical sensitivity of NiO nanoparticles by showing a distinctive absorption edge in the UV range. Using the Tauc relation, the absorption behaviour was further examined to ascertain the optical band gap energy. The discovered optical characteristics provide vital information regarding the electrical structure and prospective optoelectronic uses of the synthesised NiO. Nickel oxide nano particles (GCN 100 °C) and 2 (GCN 200 °C) on the other hand display a more semiconductor-like profile at 200 C and 300 C respectively in the absorption spectrum . The greatest absorption intensity is in the UV region but that diminishes steadily as the wavelength approaches the visible region. This reduction that identifies with the transition of the bandgap is characteristic in the fundamental absorption edge of a semiconductor. With an increase in temperature, the data shows a steady red-shift in the absorption edge. NiO (GCN 400 °C) shows a faster reduction in absorbance than Sample 1 with a minimum absorbance of 0.20 a.u. at 700 nm. Sample 1 (GCN 450 °C) has an even longer absorption edge where the optical bandgap significantly narrows with a value of 0.40 a.u. at 700 nm. The rationale behind this tendency is that a higher synthesis temperature leads to a higher structural order and polymerization, which causes an extended π -conjugation system in the GCN framework. Extremely delocalized electrons reduced the bandgap and moved the optical response to the visible region by reducing the energy required to make an electron transition.




Figure 4. Tauc plot of NiO

Conclusion

In the above discussion to much ultrafine nickel oxides nanoparticles was the successfully synthesized at the low temperature of 200°C utilizing an environmentally benign Ni(Ac)₂ solution and a straightforward wet chemical technique.. Because of the Ni-O link, the NiO NPs' FT-IR spectra only displayed a prominent vibrating all the absorption peak at about 500 cm⁻¹. According to UV-vis absorption spectra, nickel oxides nanoparticles exhibit an energy band gap of 2.44 eV and the absorption edge wavelength which is 290 nm. It is anticipated that using this environmentally friendly technique will help to enhance the manufacturing environment and achieve carbon neutrality.

References

- [1] Aartsen, M., K. Abraham, M. Ackermann, J. Adams, J. Aguilar, M. Ahlers, M. Ahrens, D. Altmann, T. Anderson and I. Ansseau. 2015. The IceCube Neutrino Observatory
- [2] Contributions to ICRC 2015 Part II: Atmospheric and Astrophysical Diffuse Neutrino Searches of All Flavors. *arXiv preprint arXiv:1510.05223*. 3(1):90.
- [3] Aazadfar, P., E. Solati and D. Dorrani. 2018. Properties of nickel oxide nanoparticles prepared by green laser irradiation of the mixture of individual suspensions. *Optical Materials*, 78: 388-395.
- [4] Afshari, S. and M. Montazer. 2018. In-situ sonosynthesis of hedgehog-like nickel nanoparticles on polyester fabric producing magnetic properties. *Ultrasonics sonochemistry*, 42: 679-688.
- [5] Ahmad, M., E. Ahmed, Y. Zhang, N. Khalid, J. Xu, M. Ullah and Z. Hong. 2013. Preparation of highly efficient Al-doped NiO photocatalyst by combustion synthesis. *Current Applied Physics*. 13(1):697-704.
- [6] Ahmed, S. 2017. Structural, optical, and magnetic properties of Mn-doped NiO samples. *Results in physics*. 7(2):604-610.
- [7] Ali, R.N., H. Naz, J. Li, X. Zhu, P. Liu and B. Xiang. 2018. Band gap engineering of transition metal in nickel oxide (NiO) nanoparticles. *Journal of Alloys and Compounds*. 744(4):90-95.
- [8] Aluri, J. and B.R. Mandava. 2016. Influence of nickel Structural and Optical Properties of NiO Nanopowders Synthesized by Sol-gel Process. *Sensors & Transducers*. 202(3):66-71.
- [9] Andrade, P., V. Silva, M. Silva and J.A. Aguiar. 2013. Synthesis and Characterization of nickel oxide (NiO) nanoparticles. *Journal of superconductivity and novel magnetism*. 26(2):2511-2514.
- [10] Arora, D., K. Ashokan, A. Mahajan, P. Kaur, G.P. Singh, S. Kumar and D. Singh. Room temperature ferromagnetism and luminescent behavior of NiO nanoparticles prepared by co precipitation method. *AIP Conference Proceedings*, 2016. 1731(1):130036
- [11] Authier, A. 2006. Dynamical theory of X-ray diffraction. *International Tables for Crystallography*. 3(1):626-646.
- [12] Bhuiyan, M. and M. Rahman. 2014. Synthesis and characterization of NiO nanoparticles. *Int. J. Res*. 3(1):67-73.
- [13] Bogner, A., P.-H. Jouneau, G. Thollet, D. Basset and C. Gauthier. 2007. A

Online ISSN

3007-3197

Print ISSN

3007-3189

<http://amresearchreview.com/index.php/Journal/about>

history of scanning electron microscopy developments: towards “wet-STEM” imaging. *Micron*. 38(4):390-401.

- [14] Borbély, A. and A.R. Kaysser-Pyzalla 2013. X-ray diffraction microscopy: emerging imaging techniques for nondestructive analysis of crystalline materials from the millimetre down to the nanometre scale. *International Union of Crystallography*. 2(3):123-230